



## MATERIAL TECHNICAL DATA SHEET

**04MC05**

**M C BLACK**

	STANDARD	UNIT	TEST CONDITION	VALUE	RANGE
MFR	ASTM D-1238	g/10'	230°C/2,16Kg	<b>8</b>	<b>±1</b>
IZOD	ASTM D-256	J/m	23°C	<b>40</b>	<b>±10</b>
FLEXURAL MODULUS	ASTM D-790	MPa		<b>800</b>	<b>±200</b>
MINERAL FILLER		%			<b>&lt;10</b>
DENSITY	ASTM D-792	g/cm <sup>3</sup>		<b>0,95</b>	<b>±0,02</b>

**APPLICATION: INJECTION MOULDING**

**PACKAGING: BIG BAGS/BAGS/OCTABINS ON PALLETS OR LOOSE IN TANK**

**AUMENTO GLOBAL FZC**

C/o NHBS Global DMCC, Unit No. I5-PF-116, Detached, Retail I5  
Plot No.: JLT-PH1-RET-I5, Jumeriah Lakes, Towers, Dubai, UAE.