



## MATERIAL TECHNICAL DATA SHEET

**04MT05**

**M T BLACK**

	STANDARD	UNIT	TEST CONDITION	VALUE	RANGE
MFR	ISO 1133	g/10'	230°C/2,16Kg	<b>5</b>	<b>±1</b>
IZOD	ASTM D-256	J/m	23°C	<b>40</b>	<b>±10</b>
FLEXURAL MODULUS	ASTM D-790	MPa		<b>800</b>	<b>±200</b>
MINERAL FILLER		%			<b>&lt;10</b>
DENSITY	ASTM D-792	g/cm <sup>3</sup>		<b>0,94</b>	<b>±0,03</b>
VICAT	ASTM D-1525	°C	50 °C/h		

**APPLICATION: INJECTION MOULDING**

**PACKAGING: BIG BAGS/BAGS/OCTABINS ON PALLETS OR LOOSE IN TANK**

### **AUMENTO GLOBAL FZC**

C/o NHBS Global DMCC, Unit No. I5-PF-116, Detached, Retail I5  
Plot No.: JLT-PH1-RET-I5, Jumeriah Lakes, Towers, Dubai,UAE.